




**Hydrophilized microporous polytetrafluorethylene membrane and production process thereof.**

**Patent number:** DE4117281  
**Publication date:** 1992-01-02  
**Inventor:** BRINK HANS-JUERGEN DR (DE); KOELLING  
HARTMUTH DR (DE); LUNKWITZ KLAUS DR (DE);  
KLATT BRUNO DR (DE); HORX MANFRED DIPL  
CHEM (DE); HERRMANN REIMUND (DE); BUEGER  
WOLFGANG DR (DE)  
**Applicant:** BITTERFELD WOLFEN CHEMIE (DE)  
**Classification:**  
- **International:** B01D71/36; B29C67/20; C08J9/26; B01D71/00;  
B29C67/20; C08J9/00; (IPC1-7): B01D67/00;  
B01D69/12; B01D71/36  
- **European:** B01D71/36; B29C67/20C; C08J9/26  
**Application number:** DE19914117281 19910527  
**Priority number(s):** DD19900342303 19900629; DD19900342304  
19900629; DD19900342300 19900629

**Also published as:**

 EP0463627 (A2)  
 EP0463627 (A3)  
 EP0463627 (B1)

[Report a data error here](#)

Abstract not available for DE4117281

Abstract of corresponding document: **EP0463627**

The invention relates to a hydrophilised, microporous membrane and to a production process therefor. The object of the invention is to produce a hydrophilised, microporous membrane made of PTFE. According to the invention, the hydrophilised microporous membrane consists of unmodified PTFE and 2.5 to 25 % by mass of highly functionalised PTFE as a largely polymer-identical hydrophilising agent. The highly functionalised PTFE is obtained by irradiation and, if appropriate, by additions of sulphites and/or carbonates. The invention also relates to production processes for the membranes.

---

Data supplied from the [esp@cenet](mailto:esp@cenet) database - Worldwide